













FM for XLPE/HFFR **Flame-retardant bedding compounds for XLPE insulation and HFFR sheathing.**

<p>■ Compound class Bedding compound</p> <p>■ Application examples: Insulation 2 XI 1 XLPE 2 YI 1 - 5 PE 9 YI 1 PP 3 GI 3 EPR</p> <p>■ Application examples: Sheathing HM 4 – 2 HFFR 2 YM 3 HDPE</p>	<p>■ Based on TPE-O</p> <p>acc. DIN / VDE 0207 part 22 acc. DIN / VDE 0207 part 2 acc. DIN / VDE 0207 part 7 acc. DIN / VDE 0207 part 20</p> <p>acc. DIN / VDE 0207 part 24 acc. DIN / VDE 0207 part 3</p>	<p>■ Characteristics Halogen-free flame retardant</p>						
<p>■ Typical applications <i>Bedding compound for cables and wire with max. 90°C operating temperature at conductor.</i></p>								
 Home	 City	 Industry						
<p>■ Features</p> <table border="0"> <tr> <td style="text-align: center;"></td> <td>For tandem process</td> <td style="text-align: center;"></td> <td>Flame retardant</td> <td style="text-align: center;"></td> <td>Halogen-free</td> </tr> </table>				For tandem process		Flame retardant		Halogen-free
	For tandem process		Flame retardant		Halogen-free			

PHYSICAL PROPERTIES

Physical properties	Unit	Typical value	Test method
Density*	g/cm ³	1,82	DIN EN ISO 1183-1A
Hardness*	Shore A	74	DIN ISO 48-4
Mooney viscosity, ML (1+4) 100°C	MU	32	DIN ISO 289-1


BURNING PROPERTIES *

Main burning properties	Unit	Typical value	Test method
Temperature index	°C	> 330	ISO 4589-3
LOI	%	63	ASTM D 2863 A
Caloric Value Hu	kJ/kg	6500	DIN 51900-2
Acid gas emission	Unit	Typical value	Test method
pH (min.)	-	6,4	IEC 60754-2
Conductivity (max.)	µS mm-1	0,83	IEC 60754-2

* pressed plaques, 100°C / 5 min.

PROCESSING GUIDE

- **Extruder type** Standard extruders for elastomeric or thermoplastic processing
- **Screw configuration** Low compression screw with L/D of 12 to 25
- **Tooling** semi-compression or tube
- **Temperature profile extruder** The profile shown below may vary slightly depending on extruder type, head design & output.



- **Maximum mass temperature** 85 – 95°C
- **Drying** Pre-drying of Melos FM Bedding Compounds is normally not necessary provided that the compound has been stored in the original sealed bags under cool (max. 30°C) and dry conditions.

STORAGE INFORMATION

- **Form & packaging** Pellets in sizes 5.5mm & 7.5mm
PE-bags (25 kg), Octabins (1.000-2.000 kg), BigBags (max. 1.250 kg)
- **Shelf life** 1 year after production

Note: The information given in this datasheet is believed to be accurate and reliable. However, no warranty, express or implied, or guarantee is given as to the suitability, accuracy, reliability or completeness of the information. This information does not hold us liable for damages or penalties resulting from following our suggestions or recommendations.

FM 0474/5 TDS ENG rev05 *05.11.2020* SK