




FM for XLPE/HFFR
Non flame-retardant bedding compound for XLPE insulation and HFFR sheathing.

<p>■ Compound class Bedding compound</p> <p>■ Application examples: Insulation 2 XI 1 XLPE 2 YI 1 - 5 PE 9 YI 1 PP 3 GI 3 EPR</p> <p>■ Application examples: Sheathing HM 4 - 2 HFFR 2 YM 3 HDPE</p>	<p>■ Based on TPE-O / EPDM</p> <p>acc. DIN / VDE 0207 part 22 acc. DIN / VDE 0207 part 2 acc. DIN / VDE 0207 part 7 acc. DIN / VDE 0207 part 20</p> <p>acc. DIN / VDE 0207 part 24 acc. DIN / VDE 0207 part 3</p>	<p>■ Characteristics Halogen-free</p>
---	--	--

■ **Typical applications**
Bedding compound for cables and wire with max. 90°C operating temperature at conductor.



■ **Features**

	For 2-step process (coilable)		Halogen-free
---	-------------------------------	---	--------------

PHYSICAL PROPERTIES

Physical properties	Unit	Typical value	Test method
Density*	g/cm ³	1,75	DIN EN ISO 1183-1A
Hardness*	Shore A	70	DIN ISO 48-4
Mooney viscosity, ML (1+4) 100°C	MU	30	DIN ISO 289-1

MECHANICAL PROPERTIES

Thermoplastic *	Unit	Typical value	Test method
Tensile strength	MPa	≥ 1,5	IEC 60811-501
Elongation at break	%	≥ 70	IEC 60811-501


ELECTRICAL PROPERTIES *

■ Major electrical properties	Unit	Typical value	Test method
Volume resistivity (at 27°C)	Ω cm	$\geq 10^{12}$	VDE 0472 Part 503
Surface resistivity (at 23°C)	Ω	$\geq 10^9$	VDE 0472 Part 502

* pressed plaques, 100°C / 5 min.

PROCESSING GUIDE

■ Extruder type	Standard extruders for elastomeric or thermoplastic processing
■ Screw configuration	Low compression screw with L/D of 12 to 25
■ Tooling	semi-compression or tube
■ Temperature profile extruder	The profile shown below may vary slightly depending on extruder type, head design & output.



■ Maximum mass temperature	105– 115°C
■ Drying	Pre-drying of Melos FM Bedding Compounds is normally not necessary provided that the compound has been stored in the original sealed bags under cool (max. 30°C) and dry conditions.

STORAGE INFORMATION

■ Form & packaging	Pellets in sizes 5.5mm & 7.5mm PE-bags (25 kg), Octabins (1.000-2.000 kg), BigBags (max. 1.250 kg)
■ Shelf life	1 year after production

Note: The information given in this datasheet is believed to be accurate and reliable. However, no warranty, express or implied, or guarantee is given as to the suitability, accuracy, reliability or completeness of the information. This information does not hold us liable for damages or penalties resulting from following our suggestions or recommendations.