


Halogen-free, thermoplastic, highly flame retardant sheathing compound for data communications, low and medium voltage cables




<p>■ Compound class Sheathing</p>	<p>■ Compound category TP</p>	<p>■ Flame retardant ATH</p>
<p>■ Standards VDE 0207 part 24 HM 2 IEC 60092-360 SHF 1</p>	<p>DIN EN 50363-8 TM7 VDE 0250 part 215 HM 5</p>	<p>DIN EN 50525-3-11 TM 7</p>
<p>■ Operating temperature [C°] -25 to 80</p>	<p>■ Oil resistance level ★</p>	

■ **Typical applications**
Halogen-free, low smoke, thermoplastic, highly flame retardant char formation compound for the sheathing of data communications, low and medium voltage cables in General Installation applications.



Installation

■ **Features**

 Flame retardant	 Halogen-free	 Low smoke
---	--	---

PHYSICAL PROPERTIES

Physical properties	Unit	Typical value	Test method
Density*	g/cm ³	1,48	DIN EN ISO 1183-1A
Hardness*	Shore D	49	DIN ISO 48-4
Melt Flow Index (150°C; 21,6kg)	g/10 min	8,5	DIN EN ISO 1133

MECHANICAL PROPERTIES **

Thermoplastic	Unit	Typical value	Test method
Tensile strength	N/mm ²	9,6	IEC 60811-501
Elongation at break	%	212	IEC 60811-501
■ After ageing in air oven 168h at 100°C ***			
Variation in tensile strength	%	+14,1	IEC 60811-401
Variation in elongation at break	%	+9,1	IEC 60811-401
■ After ageing in air oven 336h at 100°C ***			
Variation in tensile strength	%	+7,6	IEC 60811-401
Variation in elongation at break	%	+0,0	IEC 60811-401

THERMAL PROPERTIES **

■ Heat tests	Unit	Typical value	Test method
Hot pressure test: penetration 6h at 80°C	%	16	IEC 60811-508

ELECTRICAL PROPERTIES*

■ Major electrical properties	Unit	Typical value	Test method
Volume resistivity at 27°C	Ω cm	1,2 x 10¹³	DIN IEC 60093
Dielectric strength at 23°C	kV/mm	20,2	IEC 60243-1

RESISTANCE **

■ Water purified 168h at 70°C	Unit	Typical value	Test method
Variation in tensile strength	%	-9,8	IEC 60811-404
Variation in elongation at break	%	+0,6	IEC 60811-404
Variation in weight	%	+1,0	IEC 60811-404

BURNING PROPERTIES *


■ Main burning properties	Unit	Typical value	Test method
LOI *	%	38	ASTM D 2863 A
■ Acid gas emission	Unit	Typical value	Test method
Conductivity (max.)	μS/mm	1,0	IEC 60754-2
Corrosivity: pH (min.)	--	6,9	IEC 60754-2

* pressed plaques, 155°C / 5 min.

** extruded tapes

PROCESSING GUIDE

<ul style="list-style-type: none"> ■ Extruder Type ■ Screw configuration ■ Tooling ■ Temperature profile extruder 	<p>Standard extruders for elastomeric or thermoplastic materials.</p> <p>Low compression screw with L/D of 20 to 25 and compression ratio of 1:1.2</p> <p>Pressure, semi-compression or tube possible</p> <p>The profile shown below may vary slightly depending on extruder type, head design & output.</p>
---	--



<ul style="list-style-type: none"> ■ Maximum mass temperature ■ Drying 	<p>160 – 170°C</p> <p>Not necessary if the compound has been stored in original packing under cool (max. 30°C) and dry conditions. Mecoline compounds used from open packing require pre-drying during 4–6 hours at 60–70°C.</p>
--	--

STORAGE INFORMATION

<ul style="list-style-type: none"> ■ Form & packaging ■ Shelf life 	<p>Pellets in sizes 2.8mm & 5.5mm</p> <p>Moisture-resistant bags (25kg) & octabins (alu-innerliner, max. 1250kg)</p> <p>1 year after date of manufacturing</p>
--	--

Note: The information given in this datasheet is believed to be accurate and reliable. However, no warranty, express or implied, or guarantee is given as to the suitability, accuracy, reliability or completeness of the information. This information does not hold us liable for damages or penalties resulting from following our suggestions or recommendations.